

TYPICAL PROPERTIES OF
RO-11

POLYMER

NATURAL RUBBER

PHYSICAL PROPERTY	TEST METHOD	UNIT OF MEASURE	RESULT	SPECIFICATIONS
COMPRESSION DEFLECTION 25%	ASTM D1056	psi kPa	2 – 5 13.8 - 34.4	ASTM D1056-78.....RO-11 ASTM D1056-07.....1A1
DENSITY	ASTM D1056	pcf g/cm ³	22 .35	
COMPRESSION SET	ASTM D1056	%	15	
CD AFTER OVEN AGING	ASTM D1056	%	20	
COLOR	N/A	N/A	BLACK	

ADDITIONAL INFORMATION	
Service Temperature	-20°F to 160°F

For updates to this document, please refer to our website or contact customer service.

This information is furnished as a guide for selecting materials. Rubberlite Inc. disclaims liability for results or use of this information. It is the customer's responsibility to obtain and test samples when determining suitability of material for a particular application.

P.O. BOX 2965 HUNTINGTON, WEST VIRGINIA 25728
TELEPHONE (304) 525-3116 • FAX (304) 523-4316
WWW.RUBBERLITE.COM

Issue Date: 3/5/12

